

Attribute	GFRF
Weight (lb/ft²)	7-9
Nominal Thickness	5/8"
Fire Behavior	Non-combustible; 0/0 FS/SD
Flexural Strength	— (per project design; ASTM C947)
Typical Use	Exterior veneers, panels, trim
Install Complexity	Medium (engineered anchors)
Finish	Integral color, sandblast, textures

FRP	GFRG
1.75-2.25	1.5-2
3/16"	3/16" (5 mm)
Class A flame spread	Non-combustible; 0/0 FS/SD
32,100 psi	4,700 psi (ultimate)
Exterior/interior architectural shapes	Interior decorative elements
Low-Medium	Low
Gelcoat or paint-ready	Paint-ready; factory finishes